

**HUNTSMAN**


Enriching lives through innovation

# JEFFAMINE® Polyetheramine



# H

untsman's **JEFFAMINE®** amine product line offers the world's most extensive selection of polyetheramines, many of which are unavailable elsewhere. These highly versatile products contain primary amine groups attached to polyether backbones, typically based on propylene oxide (PO), ethylene oxide (EO), or a mixture of both oxides.



## FEATURES & BENEFITS

- Easy to handle
- Low viscosity and colour
- Impart increased flexibility and toughness to polymers
- Customize hydrophilicity


# JEFFAMINE®

## Polyetheramines

Our core **JEFFAMINE®** amine product line consists of monoamines, diamines, and triamines based on PPG or PEG polyether backbone structures. More recently, the addition of secondary, hindered, high-conversion, and polytetramethylene glycol (PTMEG)-based polyetheramines has increased the breadth and utility of our product line.

Our PPG-based **JEFFAMINE®** polyetheramines are easy to handle, low viscosity, and low color products. Our PEG-based amines are either liquids or waxy solids at room temperature, depending on molecular weight. Polyetheramines impart increased flexibility and toughness to a polymer network. They can also increase hydrophilicity depending on how the polyether backbone is designed.


With a broad range of molecular weights, functionality, and repeating unit design, Huntsman's **JEFFAMINE®** polyetheramines offer great scope to designing new compounds or mixtures. **JEFFAMINE®** polyetheramines are particularly important in the production of polyurea coating technologies, epoxy applications, and pigment dispersions.



# JEFFAMINE® MONOAMINES

## JEFFAMINE® M-series monoamines

JEFFAMINE® M-series polyetheramine products are monoamines based on PPG or PEG/PPG backbones. They have the following representative structure:



JEFFAMINE® M-series monoamines	MW	Average AHEW, g/eq	Application
Polypropylene glycol (PPG) based : Relatively hydrophobic. Preparation of comb polymers with poly(acrylic acid) or similar linear polymers.			
M-600	600	291	<ul style="list-style-type: none"> <li>• Molecular weight, flexibility control in polyamides</li> </ul>
M-2005	2,000	1,045	<ul style="list-style-type: none"> <li>• Molecular weight, flexibility control in polyamides</li> </ul>
Polyethylene glycol (PEG) based : Relatively hydrophilic. Formulating emulsifiers and corrosion inhibitors.			
M-1000	1,000	489	<ul style="list-style-type: none"> <li>• Ore flotation agent</li> <li>• Agricultural emulsifier</li> <li>• Emulsification of epoxy resins</li> </ul>
M-2070	2,000	1,040	<ul style="list-style-type: none"> <li>• Formulating pressure sensitive adhesives</li> <li>• Reactive dispersant</li> </ul>
M-2095	2,000	1,120	<ul style="list-style-type: none"> <li>• Modification of epoxy resins and other thermoset resins</li> <li>• Preparation of epoxy resin adducts.</li> <li>• Preparation of comb polymers with poly(acrylic acid) or similar linear polymers</li> <li>• Formulating emulsifiers, pressure sensitive adhesives, and corrosion inhibitors</li> </ul>
M-3085	3,000	1,520	



# JEFFAMINE® DIAMINES


JEFFAMINE® diamines include the D, ED, and EDR series products. The D signifies a diamine with a PPG backbone, ED signifies a diamine with a predominantly PEG backbone, and EDR designates a highly reactive diamine.

## JEFFAMINE® D-series diamines

JEFFAMINE® D-series diamines are polyether diamines based on a PPG backbone. The amines are low viscosity, low color, and miscible with a variety of solvents.



### Structure





JEFFAMINE® D-series diamines	MW	Average AHEW, g/eq	Application
D-230	230	60	<ul style="list-style-type: none"><li>• Provides tough, clear, impact resistant coatings, castings, and adhesives</li><li>• Reacts with carboxylic acids to form hot melt adhesives</li><li>• Reacts quickly with isocyanates</li><li>• Gives coatings free of surface blush prevalent with many amine curing agents</li></ul>
D-400	430	115	<ul style="list-style-type: none"><li>• Used in polyurethanes, polyureas, and termo-plastic polyamide adhesives</li></ul>
D-2000	2,000	514	<ul style="list-style-type: none"><li>• Key ingredient in the formulation of polyurea spray</li><li>• Co-reactant in epoxy systems which require increased flexibility and toughness</li><li>• Increases peel strength</li></ul>
D-2010	2,000	~514	<ul style="list-style-type: none"><li>• Key ingredient in the formulation of polyurea and RIM</li><li>• Co-reactant in epoxy systems which require increased flexibility and toughness</li></ul>
D-4000	4,000	1,000	<ul style="list-style-type: none"><li>• Co-curing agent in epoxy systems which require increased flexibility and toughness</li><li>• General polymer flexibilizer</li><li>• Increases peel strength in adhesives</li></ul>

# JEFFAMINE® DIAMINES *(cont'd...)*

## JEFFAMINE® ED-series diamines

JEFFAMINE® ED-series diamines are polyether diamines based predominantly on a PEG backbone. PEG imparts complete water solubility to each of the products in this series. JEFFAMINE® ED diamine products are miscible with a variety of solvents, and are primarily used to impart hydrophilicity to a variety of polymers and additives.



JEFFAMINE® ED-series diamines	MW	Average AHEW, g/eq	Application
ED-600	600	132	<ul style="list-style-type: none"> <li>• Preparation of epoxy resin adducts</li> <li>• Modification of polyamides for enhanced hydrophilicity</li> <li>• Hydrophilicity from polyethylene glycol</li> <li>• Reactivity from amine end group</li> </ul>
ED-900	900	250	<ul style="list-style-type: none"> <li>• Modification of polyamides for enhanced hydrophilicity</li> <li>• Preparation of biocompatible articles and coatings</li> <li>• Preparation of hydrogels with isocyanates</li> <li>• Hydrophilicity from polyethylene glycol</li> <li>• Reactivity from amine end group</li> <li>• Biocompatibility of polyethylene glycol</li> </ul>
ED-2003	2,000	575	<ul style="list-style-type: none"> <li>• Hydrophilic polymers</li> <li>• Antistatic agents</li> <li>• Epoxy modifiers</li> <li>• Textile treating</li> <li>• Water-based coatings</li> <li>• Water-soluble, water-dispersible, water-swallowable polyamides</li> <li>• Water-soluble polyurea formulations</li> <li>• Reactivity of the primary amine end groups</li> </ul>


# JEFFAMINE® DIAMINES *(cont'd...)*

## JEFFAMINE® EDR diamine

JEFFAMINE® EDR-148 diamine is much more reactive than other JEFFAMINE® diamines and triamines due to the unhindered nature of the amine groups. The high reactivity of JEFFAMINE® EDR-148 diamine makes it an excellent choice for fast curing adhesives, and for polyamide modification.



### Structure



JEFFAMINE® EDR-series diamines	MW	Average AHEW, g/eq	Application
EDR-148	148	37	<ul style="list-style-type: none"> <li>• Epoxy curing agent</li> <li>• Monomer for polyamides</li> <li>• Imparts flexibility and toughness to thermoset polymers</li> <li>• Can be formulated to cure at room temperature</li> <li>• Rapid cure at elevated temperatures</li> <li>• Excellent thermal shock resistance in cured epoxies</li> </ul>

## JEFFAMINE® THF series amines

The JEFFAMINE® THF polyetheramines products are diamines or triamines based on either a PTMEG [poly(tetramethylene ether glycol)] / PPG (polypropylene glycol) copolymer, or a predominantly PTMEG backbone. Polyetheramines of this type are useful in a variety of polymers, including cured epoxy resins, polyurea, and polyamides. Higher molecular weight polyetheramines are effective in flexibilizing and promoting adhesive peel strength in epoxy formulations. They have also been used to improve flexibility and low temperature properties for polyamides.


As with most other JEFFAMINE® polyetheramines, the amine groups in the THF-100 amine are adjacent to methyl groups, which somewhat moderates their reactivity.

New Products	Average AHEW, g/eq	Benefits
THF-100	260	<ul style="list-style-type: none"> <li>• Used in polyurethanes, polyureas, and nylons</li> </ul>

# JEFFAMINE® TRIAMINES

## JEFFAMINE® T-series triamines

JEFFAMINE® T-series polyetheramine products are triamines based on trifunctional PPG backbones. They have the following representative structure:



JEFFAMINE® T-series triamines	R	MW	Average AHEW, g/eq	Application
T-403	C <sub>2</sub> H <sub>5</sub>	440	81	<ul style="list-style-type: none"> <li>• Moderate reactivity in epoxy curing</li> <li>• Anti-sag agent for polyurethanes</li> <li>• Low color, viscosity, and vapor pressure. Can be blended with higher-viscosity curing agents to reduce their viscosity, or with cycloaliphatics to improve the elongation of higher-T<sub>g</sub> cured resins</li> <li>• Completely miscible with a wide variety of solvents, including water</li> <li>• Improves flexibility and strength</li> </ul>
T-5000	H	5,000	952	<ul style="list-style-type: none"> <li>• Crosslinker for polyurea</li> <li>• Co-reactant in epoxy systems where adhesion promotion and flexibility are important</li> <li>• Surfactant and corrosion inhibitor applications</li> <li>• Low color</li> <li>• Increased peel strength in epoxy adhesives</li> <li>• Increased toughness</li> </ul>




# SLOWER REACTING POLYETHERAMINES

For applications where a slower curing speed is beneficial, Huntsman offers two JEFFAMINE® polyetheramine products specifically designed for longer open time, low exotherm applications.

JEFFAMINE® SD-2001 amine is a difunctional secondary amine derived from JEFFAMINE® D-2000 amine. JEFFAMINE® SD-2001 amine allows for better control of open time and curing speed in applications like polyurea spray coatings, polyurea pre-polymers, and polyurea hybrid systems.

JEFFAMINE® D-205 amine is similar in AHEW and structure to JEFFAMINE® D-230 amine. However, its primary amines are more hindered, making it slower to react with epoxy groups. JEFFAMINE® D-205 amine is a good choice for epoxy applications where longer open time and a low exotherm are highly desired.



JEFFAMINE® amines	Average AHEW, g/eq	Application
SD-2001	1,000	<ul style="list-style-type: none"> <li>• Slower reactions with isocyanates – more manageable polyurea application</li> </ul>
D-205	58	<ul style="list-style-type: none"> <li>• Slower reactions with epoxy resins – more manageable large scale composites, etc</li> </ul>


# NEW POLYETHERAMINES

## JEFFAMINE® RFD-270 Amine

JEFFAMINE® RFD-270 amine is a novel amine containing both rigid (cycloaliphatic) and flexible (polyetheramine) segments in the same molecule. This product offers a unique formulating option for composites, coatings, and adhesives. When used for epoxy resin curing, this amine can provide synergistic processing and cured resin performance advantages relative to simple mixtures of polyetheramines and cycloaliphatic amines.

JEFFAMINE® RFD-270 amine can be used as an epoxy curing agent in coatings, adhesives or composites. Some of the benefits of this material are its higher glass transition temperature capability, low VOC and lower blushing.

New Products	Average AHEW, g/eq	Benefits
RFD-270	67	<ul style="list-style-type: none"><li>• Faster curing and property development, allowing reduction of any accelerator usage</li><li>• Low viscosity, color and vapor pressure</li><li>• Lower blushing or carbamation (reaction with atmospheric carbon dioxide) compared to cycloaliphatic amines</li><li>• Faster strength development than other PEA curatives and excellent mechanical properties</li><li>• Potential cost savings when formulated with JEFFSOL® PC carbonate-diluted resin vs. aliphatic epoxy-diluted resin</li><li>• Improved chemical resistance to typical acids and bases in coating applications</li></ul>




# STORAGE AND HANDLING

## Materials of Construction

JEFFAMINE® polyetheramines may be stored under air at ambient temperatures for extended periods, however a nitrogen blanket is suggested for all storage to reduce the effect of accidental exposure to high temperatures and to reduce the absorption of atmospheric moisture and carbon dioxide. It should be noted that pronounced discoloration is likely to occur at temperatures above 140°F (60°C), whatever the gaseous pad. Dispose of waste in strict accordance with local, state, and federal regulations.

At temperatures of 75-100°F (24-38°C)	
Tanks	Carbon steel
Lines, valves	Carbon steel
Pumps	Carbon steel
Atmosphere	Nitrogen or dry air
Heat exchange Surfaces	Stainless steel
Hoses	Stainless steel, polyethylene, polypropylene, TEFLON® (Elastomers such as neoprene, Buna N, and VITON® should be avoided)

At temperatures above 100°F (38°C)	
Tanks	Stainless steel
Lines, valves	Stainless steel
Pumps	Stainless steel or Carpenter 20 equivalent
Atmosphere	Nitrogen





## About Huntsman

Huntsman Corporation is a publicly traded global manufacturer and marketer of differentiated and specialty chemicals with 2022 revenues of approximately \$8 billion from our continuing operations. Our chemical products number in the thousands and are sold worldwide to manufacturers serving a broad and diverse range of consumer and industrial end markets. We operate more than 60 manufacturing, R&D and operations facilities in approximately 30 countries and employ approximately 7,000 associates within our continuing operations. For more information about Huntsman, please visit the company's website at [www.huntsman.com](http://www.huntsman.com).

## Huntsman Performance Products

Performance Products brings together innovation and world-leading process technologies to produce components used to formulate products that enhance people's lives. Our leading global positions in the manufacture and sale of amines, maleic anhydride and carbonates enable us to serve diverse consumer and industrial end markets, including energy, automotive and transportation, coatings and adhesives, construction and infrastructure, electronics, and industrial manufacturing. With 10 manufacturing facilities in North America, Europe, the Middle East and Asia, we produce and sell over 350 products to over 900 global customers, and provide extensive pre- and post-sales technical service support. The division had 2022 revenues of USD 1.7 billion.



[www.huntsman.com/pp](http://www.huntsman.com/pp)

### Global Headquarters Americas

Huntsman Corporation  
10003 Woodloch Forest Drive  
The Woodlands, Texas, 77380  
USA  
Tel : +1-281-719-6000

### Asia Pacific

Huntsman Performance Products  
No. 455 Wenjing Road  
Minhang Economic & Technological  
Development Zone  
Shanghai 200245  
P. R. China  
Tel : +86-21-3357-6588

### Europe, Middle East & Africa

Huntsman Performance Products  
Everslaan 45  
B-3078 Everberg  
Belgium  
Tel : +32-2-758-9544

**For more information, please contact  
your local Huntsman representative  
or drop us an email at  
[pp\\_enquiry@huntsman.com](mailto:pp_enquiry@huntsman.com)**

### Disclaimer

Huntsman Performance Products warrants only that its products meet the specifications agreed with the buyer. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications. While all the information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication, NO GUARANTY, WARRANTY OR REPRESENTATIONS IS MADE, INTENDED OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION OR RECOMMENDATIONS OR AS TO THE MERCHANTABILITY, SUITABILITY OR FITNESS OF ANY PRODUCTS FOR ANY PARTICULAR USE OR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE. NOTHING IN THIS PUBLICATION IS TO BE CONSTRUED AS RECOMMENDING THE INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT AND NO LIABILITY ARISING FROM ANY SUCH INFRINGEMENT IS ASSUMED. NOTHING IN THIS PUBLICATION IS TO BE VIEWED AS A LICENSE UNDER ANY INTELLECTUAL PROPERTY RIGHT. Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Performance Products containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards. Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on the manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users. Huntsman Performance Products is an international division of Huntsman International LLC. Huntsman Performance Products trades through Huntsman affiliated companies in different countries such as Huntsman Petrochemical LLC in the USA and Huntsman Holland BV in Western Europe. Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the Huntsman Terms and Conditions of Sale, which can be found at <https://www.huntsman.com/sales-terms-conditions>, which are incorporated herein by reference.

JEFFAMINE® and JEFFSOL® are registered trademarks of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries. TEFLON® is a registered trademark of The Chemours Company FC, LLC

© 2023. Huntsman Corporation or an affiliate thereof. All rights reserved.